GARR TOOL X5, G5 High Performance Milling Guide

	ICO Matavial		SFM (Vc)	CHIPLOAD PER TOOTH (Fz)							
ISO Material		HRC		3/16"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"
	COBALT BASE ALLOY	'S									
S	Powdered Metal, Stellite, Hs-21, Haynes 25/188, X-40, L-605	< 40 > 40	120 - 240 100 - 195	.0005"0015" .0004"0012"	.0008"0020" .0006"0018"	.0009"0022" .0008"0020"	.0011"0024" .0009"0022"	.0016"0034" .0012"0029"	.0018"0041" .0014"0036"	.0022"0050" .00180046	.0032"0070" .0024"0060"
	NICKEL BASE ALLOYS	S									
	Invar, Kovar, Inconel-625/718, Waspaloy, Rene, Hastelloy, A286	< 40 > 40	120 - 240 100 - 195	.0005"0015" .0004"0012"	.0008"0020" .0006"0018"	.0009"0022" .0008"0020"	.0011"0024" .0009"0022"	.0016"0034" .0012"0029"	.0018"0041" .0014"0036"	.0022"0050" .00180046	.0032"0070" .0024"0060"
	IRON BASE ALLOYS										
	Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpenter 22-b3	< 40 > 40	120 - 240 100 - 195	.0005"0015" .0004"0012"	.0008"0020" .0006"0018"	.0009"0022" .0008"0020"	.0011"0024" .0009"0022"	.0016"0034" .0012"0029"	.0018"0041" .0014"0036"	.0022"0050" .00180046	.0032"0070" .0024"0060"
	MONEL										
	Monel - 65% Nickel		160 - 290	.0005"0015"	.0008"0020"	.0009"0022"	.0011"0024"	.0016"0034"	.0018"0041"	.0022"0050"	.0032"0070"
	TITANIUM ALLOYS										
	Commercially Pure, 6Al-4V, Astm 1/2/3, 6Al-25N-4Zr-2Mo-Si		260 - 490	.0005"0015"	.0009"0019"	.0010"0020"	.0012"0026"	.0018"0038"	.0020"0046"	.0024"0054"	.0036"0078"
	5553 / Beta Titanium		195 - 365	.0004"0012"	.0009"0017"	.0010"0019"	.0012"0024"	.0018"0034"	.0020"0041"	.0024"0050"	.0032"0070"
M	STAINLESS STEELS										
	13/8, 15/5, 17-4, pH Types	< 40 > 40	290 - 490 225 - 360	.0005"0015" .0004"0011"	.0007"0018" .0006"0015"	.0008"0020" .0007"0019"	.0011"0024" .0009"0022"	.0016"0034" .0012"0029"	.0018"0041" .0014"0037"	.0022"0050" .0018"0046"	.0032"0070" .0024"0060"
	200 Series, 300 Series	< 40 > 40	355 - 555 290 - 455	.0005"0015" .0004"0010"	.0007"0018" .0006"0015"	.0008"0020" .0007"0019"	.0011"0024" .0009"0022"	.0016"0039" .0012"0029"	.0018"0046" .0014"0037"	.0022"0056" .0018"0046"	.0032"0080" .0024"0060"
	304L, 316L, Nitronic 50	< 40 > 40	325 - 520 225 - 360	.0005"0015"	.0007"0018"	.0008"0020" .0007"0019"	.0011"0024"	.0016"0034" .0012"0029"	.0018"0041" .0014"0037"	.0022"0050" .0018"0046"	.0032"0070"
	400 Series	< 40 > 40	290 - 555 225 - 425	.0005"0015" .0004"0009"	.0007"0018" .0006"0014"	.0008"0020" .0007"0019"	.0011"0026" .0009"0023"	.0016"0036" .0012"0032"	.0018"0044" .0014"0039"	.0022"0054" .0018"0048"	.0032"0074" .0024"0066"
P	HIGH STRENGTH TOO										
	A2, D2, P20, H13, S7, O1	< 40 > 40	290 - 520 195 - 425	.0006"0014" .0005"0010"	.0008"0018" .0007"0014"	.0009"0022" .0008"0018"	.0013"0026" .0012"0022"	.0016"0036" .0012"0029"	.0022"0044" .0020"0036"	.0026"0054" .0024"0046"	.0040"0074" .0036"0060"
	MEDIUM ALLOY TOO			ı							
	4140, 4340, 52100, 6150, 8620	< 40 > 40	455 - 650 325 - 490	.0006"0014" .0005"0010"	.0008"0019" .0007"0014"	.0009"0023" .0008"0018"	.0013"0027" .0012"0022"	.0016"0038" .0012"0031"	.0022"0046" .0020"0038"	.0026"0056" .0024"0046"	.0040"0078" .0036"0064"
	CARBON STEELS										
	1000's - 1018, 1020, 12L14	< 40	490 - 780	.0006"0014"	.0010"0015"	.0009"0018"	.0013"0028"	.0020"0041"	.0022"0048"	.0026"0058"	.0040"0084"
K	CAST MATERIAL										
	Steel (Malleable)		455 - 685	.0006"0019"	.0009"0023"	.0010"0025"	.0015"0029"	.0020"0044"	.0026"0051"	.0030"0060"	.0040"0090"
	Ductile Iron		455 - 685	.0006"0019"	.0009"0023"	.0010"0025"	.0015"0029"	.0020"0044"	.0026"0051"	.0030"0060"	.0040"0090"
	Gray Iron		585 - 770	.0007"0019"	.0010"0022"	.0011"0026"	.0016"0030"	.0022"0046"	.0026"0053"	.0032"0062"	.0044"0094"

	Profile/Trochoidal Milling			
Axial (ap)	up to 2xD			
Radial (ae)	5% - 25% of Dia.			



NOTE - DATA DOES NOT REFLECT CHIP THINNING.

SPINDLE INTERFACE MUST BE SCRUTINIZED WHEN USING 5/8" DIAMETER AND LARGER END MILLS

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.

