


GARR TOOL Milling Guide for TMS / TMR (HIGH EFFICIENCY MILLING)

NOTE - CHIP THINNING CALCULATION ALREADY APPLIED

CHIPLOAD PER TOOTH (Fz) AT 2% RADIAL ENGAGEMENT (USING PROGRAMMED CALCULATION - SEE PAGE 306)

SPINDLE INTERFACE MUST BE SCRUTINIZED WHEN USING 5/8" DIAMETER AND LARGER END MILLS

ISO Material	SFM (Vc)	CHIPLOAD PER TOOTH (Fz)							
		1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"	
S	TITANIUM ALLOYS								
	6Al-4V	250 - 400	.0020" - .0042"	.0030" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"	.0080" - .0143"
	5553	150 - 250	.0015" - .0028"	.0018" - .0035"	.0025" - .0043"	.0030" - .0055"	.0035" - .0065"	.0042" - .0080"	.0052" - .0095"
M	STAINLESS STEELS								
	Free Machining (303)	300 - 400	.0020" - .0042"	.0027" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"	.0080" - .0143"
	Austenitic (304 / 304L)	225 - 350	.0017" - .0035"	.0025" - .0043"	.0030" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"
Martensitic (17-4 / 416)	200 - 250	.0015" - .0028"	.0018" - .0035"	.0025" - .0043"	.0030" - .0055"	.0035" - .0065"	.0042" - .0080"	.0052" - .0095"	
P	MEDIUM ALLOY TOOL STEELS								
	8620	250 - 400	.0017" - .0035"	.0025" - .0043"	.0030" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"
	4140, D2, S7	250 - 350	.0015" - .0028"	.0018" - .0035"	.0025" - .0043"	.0030" - .0055"	.0035" - .0065"	.0042" - .0080"	.0052" - .0095"
	CARBON STEELS								
	1000 Series, A36, 12L14	300 - 500	.0020" - .0042"	.0027" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"	.0080" - .0143"
	CAST STEELS								
Steel	250 - 350	.0020" - .0042"	.0027" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"	.0080" - .0143"	
K	CAST MATERIAL								
	Ductile Iron	250 - 350	.0020" - .0042"	.0027" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"	.0080" - .0143"
	Gray Iron	250 - 350	.0020" - .0042"	.0027" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"	.0080" - .0143"
N	NON-FERROUS								
	Aluminum (6061-T6)	300 - 500	.0020" - .0042"	.0027" - .0052"	.0035" - .0065"	.0043" - .0078"	.0052" - .0095"	.0065" - .0115"	.0080" - .0143"
	Copper, Brass	175 - 350	.0017" - .0042"	.0025" - .0052"	.0030" - .0065"	.0035" - .0078"	.0043" - .0095"	.0052" - .0115"	.0065" - .0143"



ap = full flute length

ae = 2%

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.