


GARR TOOL High Performance Milling Guide for V4

NOTE - DATA DOES NOT REFLECT CHIP THINNING.

SPINDLE INTERFACE MUST BE SCRUTINIZED WHEN USING 5/8" DIAMETER AND LARGER END MILLS

	ISO Material	HRC	SFM (Vc)	CHIPLOAD PER TOOTH (Fz)								
				1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"		
S	COBALT BASE ALLOYS											
	Haynes 25/188, Stellite 21, Cobalt Chrome	< 40 > 40	90 - 185 75 - 150	.0008" - .0015" .0006" - .0013"	.0009" - .0018" .0007" - .0016"	.0011" - .0022" .0009" - .0020"	.0016" - .0030" .0012" - .0026"	.0018" - .0036" .0014" - .0032"	.0022" - .0044" .0018" - .0040"	.0032" - .0060" .0024" - .0052"		
	NICKEL BASE ALLOYS											
	Inconel-625/718, Waspaloy, Invar, Rene, Hastelloy, Monel	< 40 > 40	90 - 185 75 - 150	.0008" - .0015" .0006" - .0013"	.0009" - .0018" .0007" - .0016"	.0011" - .0022" .0009" - .0020"	.0016" - .0030" .0012" - .0026"	.0018" - .0036" .0014" - .0032"	.0022" - .0044" .0018" - .0040"	.0032" - .0060" .0024" - .0052"		
	IRON BASE ALLOYS											
	A286, Discaloy, Haynes 556, Carpenter 22, Greek Ascocolly	< 40 > 40	90 - 185 75 - 150	.0008" - .0015" .0006" - .0013"	.0009" - .0018" .0007" - .0016"	.0011" - .0022" .0009" - .0020"	.0016" - .0030" .0012" - .0026"	.0018" - .0036" .0014" - .0032"	.0022" - .0044" .0018" - .0040"	.0032" - .0060" .0024" - .0052"		
	TITANIUM ALLOYS											
	Commercially Pure, 6Al-4V, Astm 1/2/3, 6Al-25N-4Zr-2Mo-Si		200 - 375	.0009" - .0017"	.0010" - .0020"	.0012" - .0024"	.0018" - .0034"	.0020" - .0040"	.0024" - .0048"	.0036" - .0068"		
	5553 / Beta Titanium		150 - 280	.0009" - .0015"	.0010" - .0018"	.0012" - .0022"	.0018" - .0030"	.0020" - .0036"	.0024" - .0044"	.0032" - .0060"		
	M	STAINLESS STEELS										
13/8, 15/5, 17-4, pH Types		< 40 > 40	225 - 375 175 - 275	.0008" - .0015" .0006" - .0013"	.0009" - .0018" .0007" - .0016"	.0011" - .0022" .0009" - .0020"	.0016" - .0030" .0012" - .0026"	.0018" - .0036" .0014" - .0032"	.0022" - .0044" .0018" - .0040"	.0032" - .0060" .0024" - .0052"		
300 Series, 304L, Nitronic 50, Duplex, Super-Austenitic		< 40 > 40	250 - 400 175 - 275	.0008" - .0016" .0006" - .0013"	.0009" - .0018" .0007" - .0016"	.0011" - .0022" .0009" - .0020"	.0016" - .0030" .0012" - .0026"	.0018" - .0036" .0014" - .0032"	.0022" - .0044" .0018" - .0040"	.0032" - .0060" .0024" - .0052"		
400 Series - 403, 405, 420, 455		< 40 > 40	225 - 425 175 - 325	.0008" - .0016" .0006" - .0014"	.0009" - .0019" .0007" - .0017"	.0011" - .0023" .0009" - .0021"	.0016" - .0032" .0012" - .0028"	.0018" - .0038" .0014" - .0034"	.0022" - .0046" .0018" - .0042"	.0032" - .0064" .0024" - .0056"		
HIGH STRENGTH TOOL STEELS												
A2, D2, P20, H13, S7, O1	< 40 > 40	225 - 400 150 - 325	.0008" - .0016" .0006" - .0013"	.0011" - .0019" .0010" - .0016"	.0013" - .0023" .0012" - .0020"	.0016" - .0032" .0012" - .0026"	.0022" - .0038" .0020" - .0032"	.0026" - .0056" .0024" - .0040"	.0040" - .0064" .0036" - .0052"			
P	MEDIUM ALLOY TOOL STEELS											
	4140, 4340, 52100, 6150, 8620	< 40 > 40	350 - 500 250 - 375	.0008" - .0017" .0006" - .0014"	.0011" - .0020" .0010" - .0017"	.0013" - .0024" .0012" - .0020"	.0016" - .0034" .0012" - .0028"	.0022" - .0040" .0020" - .0034"	.0026" - .0048" .0024" - .0040"	.0040" - .0068" .0036" - .0056"		
	CARBON STEELS											
1000's - 1018, 1020, 12L14	< 40	375 - 600	.0010" - .0018"	.0011" - .0021"	.0013" - .0025"	.0020" - .0036"	.0022" - .0042"	.0026" - .0050"	.0040" - .0072"			
K	CAST MATERIAL											
	Ductile Iron		350 - 525	.0010" - .0018"	.0013" - .0022"	.0015" - .0026"	.0020" - .0036"	.0026" - .0044"	.0030" - .0052"	.0040" - .0072"		
	Gray Iron		450 - 590	.0011" - .0020"	.0014" - .0023"	.0016" - .0027"	.0022" - .0040"	.0028" - .0046"	.0032" - .0054"	.0044" - .0080"		

	Slotting Pocket Milling	Profiling Side Milling
Axial (ap)	up to 1.5xD	up to 2xD
Radial (ae)	1xD	5% - 15% of Dia.



NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.